

ANMASI CURATECH SP 6660
Liquid cleaner for ferrous and
non-ferrous materials,
with temporary corrosion protection

Supplier:
ANMASI A/S
Thorsvej 240
DK-7200 Grindsted

Tel.: 76 50 02 32
Mail.: info@anmasi.dk

PRODUCT DESCRIPTION

Product data

Form:	liquid
pH-value:	8.6 – 9.2
Colour:	yellow
Density g/cm ³ :	1.02 - 1.06 g/ml
Sensitive to cold below approx. °C:	+5°C

Properties

- Curatech SP 6660 is a liquid, silicate-free, mildly alkaline cleaner for ferrous and non-ferrous components.
- The surfaces cleaned with Curatech SP 6660 are equipped with a good corrosion protection.
- Curatech SP 6660 can be used both in an ultrasonic process and in a spray process.
- Above 60 °C, Curatech SP 6660 solutions no longer generate any annoying foam.

Application

The concentration for use should be 3 - 5 %.

The duration of the washing cycle depends on the system and the soiling and typically is between 4 and 8 minutes.

Temperature

The application temperature in an ultrasonic process should be between 50 - 60 °C.

The application temperature in a spray process should be between 45 - 60 °C.

Compatibility of materials

Chromium nickel steel, regular steel,, glass enamel, alkali-resistant plastics, non-ferrous metals, aluminum

ACOFT20.08.13

These notes are based on results gained from practical use to the present time. Taking into consideration individual operating conditions, deviations cannot be excluded. For this reason, we do not accept any third-party liability.